

10/540120

Amendments to the Claims:

10172001 PCT/AT 20 JUN 2005

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1 - 27. (cancelled)

28. (new) Process for the production of elements made from or comprising a latent heat storing material known as PCM provided with a sheathing, said process comprising the steps of: extruding a tube from a synthetic material, feeding said PCM continuously or intermittently, filling or introducing said PCM into the extruded tube and subdividing the PCM-filled tube into tube sections or storing the PCM-filled tube.

29. (new) The process according to claim 28, wherein said PCM-filled tube is stored coiled up.

30. (new) The process according to claim 28, feeding the PCM in liquid or granular form or as a strand in sections or in endless form.

31. (new) The process according to claim 28, wherein the step of filling the tube comprises filling the tube, after leaving the extruder nozzle and prior to entry into a cooling zone, with PCM.

32. (new) The process according to claim 28, wherein said filling step comprises filling the tube with PCM in liquid form.

33. (new) The process according to claim 28, further comprising making the tube from a plastic material and constricting the PCM-filled tube at predetermined locations in order to form said tube sections and heat sealing the constrictions.

34. (new) The process according to claim 33, passing the PCM-filled tube through a press and said constricting and heat sealing steps being performed by heated pressing tools.

35. (new) The process according to claim 34, wherein said constricting and heat sealing steps comprise constricting the tube and heat sealing at said predetermined locations one by one using reciprocating pressing tools.

36. (new) The process according to claim 34, further comprising transporting the tube between two counter-revolving endless belts equipped with pressure and heat sealing tools and said constricting and heat sealing steps being performed at the predetermined locations.

37. (new) The process according to claim 34, further comprising transporting the tube between two wheels equipped on a periphery with pressure and heat sealing tools and said constricting and heat sealing steps being performed at the predetermined locations.

38. (new) The process according to claim 32, further comprising severing the PCM-filled tube sections at narrow points so that ends of the tube sections remain sealed.

39. (new) The process according to claim 28, further comprising manufacturing a granular material consisting of PCM-filled pockets from a strand of separated tube sections.

40. (new) The process according to claim 28, further comprising affixing the PCM-filled tube sections individually or interconnected as a strand to a carrier

41. (new) The process according to claim 40, wherein said affixing step comprises affixing the PCM-filled tube sections individually or interconnected as a strand to one of a plastics non-woven fabric, a rigid plastics foil, and a flexible plastics foil.

42. (new) The process according to claim 41, further comprising arranging the tube sections parallel side-by-side on the non-woven fabric or on the rigid or flexible foil.

43. (new) The process according to claim 28, further comprising arranging and fixing the PCM-filled tube sections between a non-woven fabric and a film.

44. (new) The process according to claim 43, further comprising bringing an endless non-woven fabric and an endless strand of PCM-filled tube sections together in a nip of a roller pair, interconnecting said fabric and said endless strand in said nip, and coating the tube filled sections with the film from an extruder nozzle on a side facing away from the non-woven fabric.

45. (new) The process according to claim 43, further comprising drawing the film over the tube sections up to the non-woven

fabric and fixing the film on the non-woven fabric between adjacent tube sections.

46. (new) The process according to claim 43, wherein the non-woven fabric brings together tube sections individually fed from a hopper in a nip of a roller pair and further comprising coating the tube sections in the nip with the film from an extruder nozzle and fixing the film between the tube sections by adhesively bonding the film to the non-woven fabric.

47. (new) An element comprising a latent heat storing material denoted as PCM, said element being manufactured from an endless PCM-filled tube made of synthetic material as tear-resistant, impervious and diffusion-proof sheathing and being designed as a section of a strand to be subdivided into sections as finished or semi-finished product, wherein the section forms an individually separated and sealed element.

48. (new) The element according to claim 47, wherein the PCM-filled tube is constricted and heat sealed at predetermined intervals in order to form tube sections forming a coherent strand.

49. (new) The element according to claim 48, wherein the tube sections form a granular material consisting of PCM-filled pockets.

50. (new) The element according to claim 47, wherein the PCM-filled tube sections individually or forming a continuous strand are affixed to a carrier

51. (new) The element according to claim 50, wherein said carrier is one of a non-woven fabric of plastics, a flexible plastics foil, and a rigid plastics foil.

52. (new) The element according to claim 47, wherein a phase change temperature of the PCM is adapted to an intended use.

53. (new) The element according to claim 52, wherein said phase change temperature is in the range of 15 - 40°C.

54. (new) The element according to claim 52, wherein said phase change temperature is in the range of 20 - 35°C.

55. (new) The element according to claim 47, wherein the sheathing is flexible and permits shape variations of the elements consisting of PCM in a pulverised, granular, liquid or paste-like state.

56. (new) The element according to claim 55, wherein the sheathing is balloon-like.

57. (new) The element according to claim 55, wherein the sheathing is tubular.

58. (new) The element according to claim 47, wherein the sheathing is multi-layered.

59. (new) The element according to claim 47, wherein the PCM possesses a latent heat of at least 50KJ/kg.

60. (new) The element according to claim 47, wherein the PCM consists of a paraffin mixture.

61. (new) The element according to claim 60, wherein the paraffin mixture is selected from the group consisting of eicosane, nonadecane and oktadecane.

62. (new) The element according to claim 47, wherein the PCM is selected from the group consisting of a salt and a salt hydrate.

63. (new) The element according to claim 62, wherein the PCM is a salt hydrate selected from the group consisting of calcium chloride hexahydrate and lithium nitrate-trihydrate.